



US008772181B2

(12) **United States Patent**
Noda et al.

(10) **Patent No.:** **US 8,772,181 B2**
(45) **Date of Patent:** **Jul. 8, 2014**

(54) **METHOD FOR PRODUCING GRAPHENE,
GRAPHENE PRODUCED ON SUBSTRATE,
AND GRAPHENE ON SUBSTRATE**

(75) Inventors: **Suguru Noda**, Tokyo (JP); **Soichiro Takano**, Tokyo (JP)

(73) Assignee: **Japan Science and Technology Agency**,
Saitama (JP)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/001,171**

(22) PCT Filed: **Feb. 27, 2012**

(86) PCT No.: **PCT/JP2012/054810**

§ 371 (c)(1),

(2), (4) Date: **Sep. 12, 2013**

(87) PCT Pub. No.: **WO2012/118023**

PCT Pub. Date: **Sep. 7, 2012**

(65) **Prior Publication Data**

US 2013/0341792 A1 Dec. 26, 2013

(30) **Foreign Application Priority Data**

Feb. 28, 2011 (JP) 2011-042781

(51) **Int. Cl.**

H01L 21/469 (2006.01)

H01L 29/08 (2006.01)

(52) **U.S. Cl.**

USPC **438/781**; 257/40

(58) **Field of Classification Search**

USPC 438/82, 99, 623, 781; 423/447, 460;
257/40, 642

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,641,915 B2 * 2/2014 Kim et al. 216/37
2010/0218801 A1 * 9/2010 Sung et al. 136/244
2011/0243830 A1 * 10/2011 Ozaki et al. 423/445 R

FOREIGN PATENT DOCUMENTS

JP 2009-143799 A 7/2009
JP 2010-089996 A 4/2010
WO 2010/001686 A1 1/2010
WO 2010/043716 A1 4/2010

OTHER PUBLICATIONS

Kenkyu Yo et al, "Kinzoku Yuki Kesshoka ni yoru Tanso Usumaku
kara no Graphene Sakusei", The Society of Chemical Engineers,
Japan Kanto Shibu Taikai Kenkyu Happyo Koen Yoshisyu, vol. 2010,
Jul. 19, 2010, p. 79.

Keun Soo Kim et al., Large-scale pattern growth of graphene films for
stretchable transparent electrodes, Nature, vol. 457, pp. 706-710,
Macmillan Publishers Limited., Feb. 5, 2009.

* cited by examiner

Primary Examiner — Calvin Lee

(74) *Attorney, Agent, or Firm* — Enshan Hong VLP Law
Group LLP

(57) **ABSTRACT**

A production method for producing graphene on a substrate,
and the like are provided. According to the method, in a
forming step heating is conducted to a solid solution tempera-
ture at which a solid solution of carbon dissolved in a metal is
able to be formed, and a solid solution layer (505) composed
of the solid solution on a substrate (103) is formed; and in a
removing step graphene (102) is grown on the substrate (103)
by removing the metal from the solid solution layer (505)
while maintaining the heating to the solid solution tempera-
ture. As a solvent for dissolving carbon a metal composed of
a single element as well as various alloys are applicable. The
graphene (102) touches directly the substrate (103), by
removing the metal from the solid solution layer (505) by
supplying an etching gas.

14 Claims, 34 Drawing Sheets





FIG. 1A




FIG. 1B




FIG. 2




FIG. 3




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E




FIG. 5F




FIG. 5G




FIG. 5H




FIG. 5I




FIG. 5J




FIG. 5K




FIG. 5L




FIG. 5M




FIG. 5N




FIG. 5O





FIG. 6A






FIG. 7C




FIG. 7D




FIG. 7E




FIG. 7F




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D




FIG. 8E




FIG. 8F




FIG. 8G




FIG. 8H




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 9E




FIG. 9D




FIG. 9F




FIG. 9G




FIG. 9H




FIG. 9I




FIG. 10A





FIG. 10B




FIG. 10C




FIG. 10D




FIG. 10E




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 11D




FIG. 11E




FIG. 11F




FIG. 11G




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 12D




FIG. 12E




FIG. 12F




FIG. 13A




FIG. 13B




FIG. 14




FIG. 15A




FIG. 15B




FIG. 16A




FIG. 16B




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21





FIG. 22



1

METHOD FOR PRODUCING GRAPHENE, GRAPHENE PRODUCED ON SUBSTRATE, AND GRAPHENE ON SUBSTRATE

PRIORITY CLAIM

This is a U.S. national stage of application No. PCT/JP2012/054810, filed on Feb. 27, 2012. Priority is claimed on the following application: Country: Japan, Application No.: 2011-042781, Filed: Feb. 28, 2011, the content of which is incorporated here by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a production method for graphene, graphene produced on a substrate, and graphene on a substrate.

2. Description of the Related Art

Graphene is carbon atoms hexagonally-arranged through sp^2 bonds forming a monolayer sheet-like crystal, or a plurality of the sheets piled up, which is superior in electrical characteristic, and mechanical strength, and is expected to be applied to various devices.

CITATION LIST

For example, a study is in progress for applying the electrical conductivity of graphene to an electronic element, a semiconductor element, an electronic circuit, an electrical circuit, an integrated circuit, and the like.

Patent Literature

Namely, such applications of graphene are conceivable as an application to a transparent electrode for a liquid crystal display, a touch screen, a solar cell, and the like, an application to wiring, an electrode, and a terminal for a semiconductor integrated circuit or a flexible integrated circuit, and an application to a transfer channel for an electron or a positive hole between a source and a drain of a field effect transistor.

For this purpose, it is required to grow graphene on various substrates (a silicon dioxide substrate, a silicon substrate provided with a silicon dioxide layer on the surface, as well as those having a multilayer structure composed of an insulator, a semiconductor, and a conductor). Accordingly, various production techniques for graphene on a substrate have been proposed.

For example, Non Patent Literature 1 has proposed a technique, by which a nickel thin-film is formed on a substrate as a catalyst, carbon is dissolved in the nickel thin-film by a thermal chemical vapor deposition (CVD) method, then graphene is precipitated on the nickel thin-film by quenching, thereafter the nickel thin-film is etched and the graphene is transcribed to another substrate to form patterned graphene on the substrate as a transparent electrode.

CITATION LIST

Non Patent Literature

Non Patent Literature 1: Keun Soo Kim, et al., "Large-scale pattern growth of graphene films for stretchable transparent electrodes", Nature, vol. 457, pp. 706-710, MacMillan Publishers Limited., May 2, 2009

SUMMARY OF INVENTION

However, once graphene is formed, a catalyst metal is sandwiched between the graphene and a substrate, removal of

2

the metal become very cumbersome and it is possible that complete removal become often difficult.

Further, since a defect is generated when graphene is transcribed, a fine pattern is able to be hardly formed.

Therefore, a technique for producing graphene attached directly to a substrate surface without remaining a catalyst metal on the substrate surface has been strongly sought-after.

Further, in graphene produced according to a conventional art, crystals grow randomly from a catalyst metal so that graphene forms an inhomogeneous polycrystalline film with randomly formed crystal grain boundaries.

Therefore, a technique for limiting a zone where crystal grain boundaries are formed to an intended zone by regulating the growth of graphene, and producing a largest possible single crystal graphene has been sought-after.

For finding solutions therefor, an object of the present invention is to provide a production method for graphene, graphene produced on a substrate, and graphene on a substrate.

A production method for graphene with respect to the first aspect of the present invention is constituted with a forming step for conducting heating to a solid solution temperature at which a solid solution of carbon dissolved in a metal is able to be formed, and forming a solid solution layer comprising the solid solution on the substrate; and a removing step for removing the metal from the solid solution layer while maintaining the heating to the solid solution temperature.

A solid solution means herein a mixture of a plurality of substances dissolving each other forming as a whole a homogeneous solid. In general a main component of a solid solution is called as a solvent of the solid solution, and other substances are called as solutes of the solid solution.

According to the present invention, a solid solution is formed with a metal as a solvent and carbon as a solute, but such formation of a solid solution is possible only within a certain temperature range. The temperature range is called as a solid solution temperature. For a solid solution temperature, the lower limit or the upper limit thereof is determined by a combination of materials or a composition of solvents.

By removing a metal while maintaining the heating of a solid solution, carbon that is not able to remain dissolved any more in the solid solution precipitates keeping its high mobility to grow graphene on a substrate. On this occasion, high mobility carbon moves to graphene first nucleated by removal of a metal, and becomes incorporated to increase the crystal grain size of the graphene, while suppressing new nucleation of the graphene.

As a metal to be used as a solvent for a solid solution according to the present invention, it is possible that a pure metal composed of a single metal element, an alloy composed of a plurality of metal elements, and also an alloy composed of a metal element and a nonmetallic element be applied. Namely, it is possible that a solvent, which dissolves carbon as a solute for a solid solution and contains a metal as its main component, be applied as a solvent for a solid solution.

Further, it is possible that a production method according to the present invention be so constituted that, in the forming step, a reducing agent that is able to reduce an oxide of the metal is supplied, and in the removing step, the metal contained in the solid solution layer is removed by supplying an etching gas. If etching is carried out long enough to remove all of metals contained in a solid solution layer according to the production method, graphene comes to touch directly a substrate without intercalating a metal. Due to various causes it is possible that a metal oxide be generated in a solid solution layer, but according to the present production method, a sup-

plied reducing agent prevents the metal oxide from remaining on a substrate, and good quality graphene is able to be obtained.

Further, it is possible that a production method according to the present invention be so constituted, that, in the forming step, an initial layer comprising carbon is formed on the substrate, a metallic layer comprising the metal is formed on the formed initial layer, and the formed initial layer and the formed metallic layer are heated to the solid solution temperature to form the solid solution layer. Namely, in this production method, an initial layer is composed of carbon alone, or a material containing carbon (for example, mixture of carbon and a metal), and a metallic layer is composed of a metal alone, or a material containing a metal (for example, an alloy of metals, or an alloy of a metal and a nonmetal). First the initial layer is formed, and then the metallic layer is formed.

Further, it is possible that a production method according to the present invention be so constituted, that, in the forming step a metallic layer comprising the metal is formed on the substrate, an initial layer comprising carbon is formed on the formed metallic layer, and the formed initial layer and the formed metallic layer are heated to the solid solution temperature to form the solid solution layer. Namely, in this production method, as in the above mode, an initial layer is composed of carbon alone, or a material containing carbon (for example, mixture of carbon and a metal), and a metallic layer is composed of a metal alone, or a material containing a metal (for example, an alloy of metals, or an alloy of a metal and a nonmetal). However, in the current production method, a metallic layer is first formed and then the initial layer is formed.

Further, it is possible that a production method according to the present invention be so constituted, that, in the forming step an initial layer comprising a mixture of the metal and carbon is formed on the substrate, and the formed initial layer is heated to the solid solution temperature to form the solid solution layer. Namely, in this production method, different from the above modes, a mixture of carbon and a metal is used as an initial layer. Namely, a mixture of carbon and a metal is heated to form a solid solution layer, in which carbon is dissolved in a metal. In the current production method formation of an independent metallic layer is not necessary.

Further, it is possible that a production method according to the present invention be so constituted, that, in the forming step the initial layer is formed into a predetermined pattern, so as to form the graphene in the predetermined pattern.

Further, it is possible that a production method according to the present invention be so constituted, that, in the forming step the initial layer is formed to cover all or a part of a surface of the substrate, so as to form the graphene into a uniform continuous film covering all or a part of the surface of the substrate.

Further, it is possible that a production method according to the present invention be so constituted, that a concentration distribution in a direction parallel to a surface of the substrate among concentration distributions of the carbon in the solid solution layer is made inhomogeneous, so as to grow the graphene in the direction parallel to the surface of the substrate. In this regard, it is possible that the concentration distribution in a direction not parallel to the surface of the substrate be uniform or inhomogeneous.

Further, it is possible that a production method according to the present invention be so constituted, that the thickness of at least one of the formed initial layer and the formed metallic layer is made inhomogeneous, so as to make a concentration distribution in a direction parallel to a surface of the substrate

among concentration distributions of the carbon in the solid solution layer inhomogeneous, and to grow the graphene in the direction parallel to the surface of the substrate. According to the present invention, a solid solution layer is formed from an initial layer and a metallic layer, because carbon in the initial layer is dissolved by heating in a metal in the metallic layer. In this case, it is desirable to adjust a heating condition, so that, in forming a solid solution layer, carbon is able to move over a submicrometer distance to mix with a substrate in a vertical direction, but is not able to move a few μm or more to mix in a direction parallel to a substrate. With such an adjustment, and, for example, in the event that the thickness of an initial layer is made uniform and the thickness of a metallic layer is made nonuniform, the carbon concentration of a solid solution layer at an area, where the metallic layer has been thick, becomes low, and at an area, where the metallic layer has been thin, the carbon concentration of a solid solution layer becomes high. Furthermore, in the event that the thickness of an initial layer is made nonuniform and the thickness of a metallic layer is made uniform, the carbon concentration of a solid solution layer at an area, where the metallic layer has been thick, becomes high, and at an area, where the metallic layer has been thin, the carbon concentration of a solid solution layer becomes low. When a metal is removed, graphene grows from a zone where the carbon concentration is high toward a zone where the carbon concentration is low. In this regard, it is possible that the concentration distribution in a direction not parallel to a surface of the substrate be either uniform or inhomogeneous.

Further, it is possible that a production method according to the present invention be so constituted, that the thickness of the formed metallic layer is provided with a gradient, so as to grow the graphene in the direction of a component parallel to the surface of the substrate among directions of the gradient. The current invention is a favorable embodiment of the above inventions for attaining reduction of the production cost or the like, by means of a construction technique by which a gradient is provided in the thickness of the metallic layer.

Further, it is possible that a production method according to the present invention be so constituted, that the metallic layer comprises a first region extending parallel over a surface of the substrate and a second region extending parallel over a surface of the substrate, the two regions being connected by a constriction, the first region having smaller thickness of the metallic layer than the second region, and the second region being provided with a gradient in the thickness of the metallic layer, which increases with the distance from the constriction.

Further, it is possible that a production method according to the present invention be so constituted, that a concentration distribution of the supplied etching gas in a direction parallel to a surface of the substrate is made inhomogeneous, so as to grow the graphene in the direction parallel to the surface of the substrate. In this regard, it is possible that the concentration distribution in a direction not parallel to a surface of the substrate be either uniform or inhomogeneous.

Further, it is possible that a production method according to the present invention be so constituted, that the substrate is composed of a monolayer or multilayers.

Further, it is possible that a production method according to the present invention be so constituted, that the substrate is a silicon dioxide substrate or a silicon substrate provided with a silicon dioxide layer on a surface, the metal is iron, nickel, cobalt, or an alloy comprising the same, and the etching gas is chlorine.

A production method for graphene with respect to the second aspect of the present invention is so constituted that line-shaped graphene grown in a first direction parallel to a

5

surface of a substrate and directly attached to the surface is produced by the above production method, and planar graphene grown from the line-shaped graphene in a second direction parallel to the surface and directly attached to the surface is produced by the above production method.

Graphene with respect to the third aspect of the present invention is so constituted that the same is produced on a substrate by the above production method.

Graphene on a substrate with respect to the fourth aspect of the present invention is so constituted that the graphene on a substrate is directly attached to a surface of the substrate, the crystal grain size of the graphene on a substrate in a first direction parallel to the surface is the largest among crystal grain sizes of the graphene on a substrate in any other directions parallel to the surface, and the crystal grain size of the graphene on a substrate in the first direction is larger than the crystal grain size of the graphene in a direction perpendicular to the surface.

Graphene on a substrate with respect to the fifth aspect of the present invention is so constituted that the graphene on a substrate is directly attached to a surface of the substrate, the graphene on a substrate has a plurality of crystal grain boundaries in a first direction parallel to the surface, the graphene on a substrate has a plurality of crystal grain boundaries in a second direction parallel to the surface, and the graphene on a substrate constitutes a single crystal inside each region surrounded by the crystal grain boundaries.

Further, it is possible that the graphene on a substrate according to the present invention be so constituted that the first direction is orthogonal to the second direction, the intervals of crystal grain boundaries along the first direction are constant, and the intervals of crystal grain boundaries along the second direction are constant. Further, with respect to graphene on a substrate according to the present invention, it is possible that the substrate be constituted with a monolayer or multilayers.

Further, it is possible that graphene on a substrate according to the present invention be so constituted that the thickness of the graphene on a substrate is 300 nanometers or less and the crystal grain size of the graphene on a substrate in the first direction is 30 μm or more.

Further, it is possible that graphene on a substrate according to the present invention be so constituted that the graphene on a substrate has a predetermined pattern and the line width of the pattern is 10 μm or less.

Further, with respect to graphene on a substrate according to the present invention, it is possible that the predetermined pattern be so constituted to form wiring, an electrode, or a terminal for a current path or voltage application, or a channel for transferring an electron or a positive hole.

Moreover, a graphene device provided with the graphene on a substrate and the substrate attached directly with the graphene on a substrate is able to be constituted.

According to the present invention, a production method for graphene, graphene produced on a substrate, and graphene on a substrate is able to be provided.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1A is a plan view showing the first example of graphene on a substrate according to the present embodiment;

FIG. 1B is a cross-sectional view showing the first example of graphene on a substrate according to the present embodiment;

FIG. 2 is a plan view showing the second example of graphene on a substrate according to the present embodiment;

6

FIG. 3 is a plan view showing the third example of graphene on a substrate according to the present embodiment;

FIG. 4 is a diagram depicting a cross-section of a field effect transistor utilizing graphene on a substrate according to the present embodiment;

FIG. 5A is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5B is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5C is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5D is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5E is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5F is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5G is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5H is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5I is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5J is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5K is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5L is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5M is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5N is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 5O is a cross-sectional view for illustrating a process for producing a graphene device;

FIG. 6A is a plan view illustrating line-shaped graphene and the growing direction thereof;

FIG. 6B is a plan view illustrating planar graphene and the growing direction thereof;

FIG. 7A is a diagram illustrating a process of a production method for a graphene device;

FIG. 7B is a diagram illustrating a process of a production method for a graphene device;

FIG. 7C is a diagram illustrating a process of a production method for a graphene device;

FIG. 7D is a diagram illustrating a process of a production method for a graphene device;

FIG. 7E is a diagram illustrating a process of a production method for a graphene device;

FIG. 7F is a diagram illustrating a process of a production method for a graphene device;

FIG. 8A is a diagram illustrating a process of a production method for a graphene device;

FIG. 8B is a diagram illustrating a process of a production method for a graphene device;

FIG. 8C is a diagram illustrating a process of a production method for a graphene device;

FIG. 8D is a diagram illustrating a process of a production method for a graphene device;

FIG. 8E is a diagram illustrating a process of a production method for a graphene device;

FIG. 8F is a diagram illustrating a process of a production method for a graphene device;

FIG. 8G is a diagram illustrating a process of a production method for a graphene device;

FIG. 8H is a diagram illustrating a process of a production method for a graphene device;

7

FIG. 9A is a diagram illustrating a process of a production method for a graphene device;

FIG. 9B is a diagram illustrating a process of a production method for a graphene device;

FIG. 9C is a diagram illustrating a process of a production method for a graphene device;

FIG. 9D is a diagram illustrating a process of a production method for a graphene device;

FIG. 9E is a diagram illustrating a process of a production method for a graphene device;

FIG. 9F is a diagram illustrating a process of a production method for a graphene device;

FIG. 9G is a diagram illustrating a process of a production method for a graphene device;

FIG. 9H is a diagram illustrating a process of a production method for a graphene device;

FIG. 9I is a diagram illustrating a process of a production method for a graphene device;

FIG. 10A is a diagram illustrating a process of a production method for a graphene device;

FIG. 10B is a diagram illustrating a process of a production method for a graphene device;

FIG. 10C is a diagram illustrating a process of a production method for a graphene device;

FIG. 10D is a diagram illustrating a process of a production method for a graphene device;

FIG. 10E is a diagram illustrating a process of a production method for a graphene device;

FIG. 11A is a diagram illustrating a process of a production method for a graphene device;

FIG. 11B is a diagram illustrating a process of a production method for a graphene device;

FIG. 11C is a diagram illustrating a process of a production method for a graphene device;

FIG. 11D is a diagram illustrating a process of a production method for a graphene device;

FIG. 11E is a diagram illustrating a process of a production method for a graphene device;

FIG. 11F is a diagram illustrating a process of a production method for a graphene device;

FIG. 11G is a diagram illustrating a process of a production method for a graphene device;

FIG. 12A is a diagram illustrating a process of a production method for a graphene device;

FIG. 12B is a diagram illustrating a process of a production method for a graphene device;

FIG. 12C is a diagram illustrating a process of a production method for a graphene device;

FIG. 12D is a diagram illustrating a process of a production method for a graphene device;

FIG. 12E is a diagram illustrating a process of a production method for a graphene device;

FIG. 12F is a diagram illustrating a process of a production method for a graphene device;

FIG. 13A is a graph showing a Raman spectrum in the event a solid solution layer is formed and then quenched without etching;

FIG. 13B is a graph showing a Raman spectrum in the event a production method according to the present embodiment is used;

FIG. 14 is graphs showing features of Raman spectra for metallic layers with various thicknesses, which are cooled after annealing, after etching for 3 min, and after etching for 30 min;

FIG. 15A is a diagram showing an atomic force microscope image of patterned graphene produced according to parameters A;

8

FIG. 15B is a diagram showing an atomic force microscope image of patterned graphene produced according to parameters B;

FIG. 16A is an enlarged view showing an atomic force microscope image of patterned graphene produced according to parameters B;

FIG. 16B is a diagram showing an electrical current map of patterned graphene produced according to parameters B;

FIG. 17 is a diagram illustrating a process of a production direction for a graphene device according to the present embodiment;

FIG. 18 is graphs showing features of Raman spectra in the event a carbon layer is formed on a metallic layer and cooled after annealing, and after etching for 3 min;

FIG. 19 is graphs showing features of Raman spectra corresponding to heating temperatures;

FIG. 20 is a graph showing features of a Raman spectrum of a sample prepared by a mode performing reduction of a metal oxide in forming a solid solution layer;

FIG. 21 is a scanning electron microscope picture showing final features of a graphene crystal when the hydrogen partial pressure is 1 Torr; and

FIG. 22 is a scanning electron microscope picture showing final features of a graphene crystal when the hydrogen partial pressure is 20 Torr.

DETAILED DESCRIPTION OF THE PRESENTLY PREFERRED EMBODIMENTS

Embodiments of the present invention will be described below. In this regard, the embodiments described below are only for explanatory purpose and not for limiting the scope of the present inventions. Consequently, those skilled in the art are able to adopt an embodiment in which any of the elements or all of the elements have been replaced with equivalent elements, and such an embodiment is considered to be falling within the scope of the present invention.

In the figures herein dimensions and shapes are appropriately expressed exaggeratedly to facilitate understanding.

Example 1

FIG. 1A is a plan view showing the first example of graphene on a substrate according to the present embodiment, and FIG. 1B is a cross-sectional view showing the first example of graphene on a substrate according to the present embodiment. The example will be described below referring to the above figures.

As shown in the figures, the graphene **102** forms a layer directly attached to a surface of the substrate **103**. The thickness of graphene **102** producible according to a conventional technique was maximum approx. 30 nanometers, but the thickness of graphene **102** according to the present embodiment is able to be selected at a desired thickness not beyond 300 nanometers.

It is possible that the substrate **103** be a silicon dioxide substrate or a silicon substrate provided with a silicon dioxide layer on a surface, or moreover have a multilayer structure. In the case of a multilayer structure, it is possible that each layer be, for example, appropriately provided with a conductor, a semiconductor, or an insulator to form a semiconductor circuit, an electronic circuit, or an electrical circuit.

By attaching the graphene **102** directly to a surface of the substrate **103**, a graphene device **101** (graphene element) is formed as a whole. In this regard, an "element" means herein

a component that preforms a function, and a “device” means a component constituted with one or plural elements, respectively.

The graphene **102** of the first example forms a single crystal in a range surrounded by crystal grain boundaries **104** (in the current figure, depicted as thick dotted lines). The regions surrounded by crystal grain boundaries **104** have different shapes each other, this is because the graphene **102** has grown randomly on a surface of the substrate **103**. Approximately, the center of each region corresponds to the initiation point for precipitation of the graphene **102**.

Although the graphene **102** is indicated by hatching in the figures, the hatching does not mean a crystal forming direction of the graphene **102**. As described above, crystal grain boundaries **104** are generated in the graphene **102** in a direction along the surface of the substrate **103**, however in the vertical direction to the surface of the substrate **103** the crystal structures of the graphene **102** are uniform at almost all places.

Although the crystal grain boundaries **104** extend from a surface of the graphene **102** to a surface of the substrate **103**, depiction thereof is omitted appropriately to facilitate understanding in FIG. 1B and the following figures.

FIG. 2 is a plan view showing the second example of graphene on a substrate according to the present embodiment. The example will be described below referring to the figure.

In the graphene device **101** shown in the figure, crystal grain boundaries **104** of the graphene **102** is formed to a regular grid at constant intervals in a vertical method (a first direction) and a horizontal method (a second direction). Namely, the graphene **102** composed of square single crystals covers the substrate **103**.

Since, as described below, an initiation point or a direction of growth of the graphene **102** on the substrate **103** is able to be regulated according to the present invention, the crystal grain boundaries **104** are able to be formed to various shapes, such as square and rectangle. Further, the area of a single crystal of the graphene **102** is able to be made by far larger than that in the past. Specifically, the crystal grain size of a single crystal of the graphene **102** is able to be made 30 μm or more.

The first direction and the second direction of extension of the crystal grain boundaries **104** cross typically at a right angle as described above, however if they cross obliquely at a constant angle, the shape of a single crystal of the graphene **102** becomes parallelogram. Further, the intervals between the crystal grain boundaries **104** are not required to be constant.

By applying a production method according to the present invention, growth of graphene **102** is able to be made more stable than in the past.

The crystal grain size of the graphene **102** is maximal in a growing direction of the graphene **102** in producing the graphene device **101**.

As described above, in the graphene device **101** according to the present embodiment, the surface of the substrate **103** is covered by large single crystals of graphene **102**, and one of characteristics of the same is that the crystal grain boundaries **104** of the graphene **102** are few and located at predetermined places and the crystal grain sizes are large.

If the size of a substrate **103** is made small, and the environment for producing the graphene device **101** is set appropriately, and the growth of graphene **102** is carried out over a long time period, it is not impossible for a single crystal of the graphene **102** to cover the entire surface of the substrate **103**.

Such graphene device **101**, in which graphene **102** covers the entire surface of the substrate **103**, is able to be applied, in

view of the electrical conductivity and the mechanical strength of graphene **102**, as described below, as a pattern; or used as a substrate product to be fabricated to a various devices, such as a semiconductor integrated circuit, and a MEMS; a transparent electrode for a solar cell, a surface-emitting light, a flat panel display, and a touch screen; and the like.

FIG. 3 is a plan view showing the third example of graphene on a substrate according to the present embodiment. The example will be described below referring to the figure.

In the graphene device **101** shown in the figure, the graphene **102** does not cover the entire surface of the substrate **103**, but forms a pattern. Since graphene **102** is electrically conductive, the pattern is able to be applied to various wiring, terminals, electrodes, and the like. The pattern shape is not limited to that shown in the figure, and it is possible that the pattern shape be selected discretionarily.

By a conventional technique, in which a pattern of graphene is produced in advance and then transcribed, in producing a detailed pattern of micrometer scale, damages will occur during transcription. Meanwhile, as described below by a production method according to the present application, a pattern with the line width of 10 μm or less is able to be formed on a substrate. Further, by a conventional technique, in which graphene is once transcribed to a broad region of a substrate and then etched for patterning, the substrate is damaged in etching the graphene, which is especially problematic for application to a multilayer substrate. Meanwhile, by a production method according to the present application as described below, a simplified production process without etching of graphene is adopted, and therefore there occurs no such a problem.

Therefore the pattern is able to substitute for not only fine wiring by copper or aluminum but also a transparent electrode by indium tin oxide (ITO).

For example, in the case of a liquid crystal display, an application, in which glass is used as a substrate **103** and a transparent electrode composed of graphene **102** is formed directly on a surface of the glass in a pattern shape, is possible.

Further, the substrate **103** is not limited to a monolayer, and a multilayer structure provided with wiring or an object of conduction in each layer is possible.

Namely, it is possible that a substrate **103** be formed as a multilayer structure composed of semiconductors, wiring, insulation films in a semiconductor integrated circuit, and it is possible that graphene **102** be utilized as fine wiring connecting the respective elements in the multilayer structure.

Additionally, if wiring or an object of conduction is placed on the back side of a substrate **103**, wiring penetrating the substrate **103** is to be provided and the wiring is able to be connected by graphene **102**.

Further, graphene **102** is able to be utilized as a transfer path for an electron or a positive hole, such as channel between a source and a drain of a field effect transistor.

FIG. 4 is a diagram depicting a cross-section of a field effect transistor utilizing graphene on a substrate according to the present embodiment. The example will be described below referring to the figure.

As shown in the figure, the graphene **102** on the substrate **103** constitutes a transfer channel for an electron or a positive hole from a source electrode **401** to a drain electrode **402**. A gate electrode **404** is placed intercalating the graphene **102** and an insulator **403**, and by regulating the voltage applied to the gate electrode **404** the flow rate of an electron or a positive hole moving through the graphene **102** is regulated. As above, the graphene device **101** of the present mode functions as a field effect transistor.

11

Example 2

According to a conventional production method, detached graphene **102** was transcribed on to a substrate **103**, or graphene **102** was precipitated on to a metal catalyst on a substrate **103** and then the metal catalyst was etched.

On the other hand, according to the present invention, graphene **102** with a large crystal grain size as disclosed in Example 1 is able to be directly formed on a surface of a substrate **103**. First, the principle of the present production method will be described.

In the present embodiment, firstly to form a solid solution layer dissolving carbon in a metal, such as iron, cobalt, and nickel, on a surface of a substrate **103**, the same are heated to a solid solution temperature.

Continuing heating, the metal contained in the solid solution layer is removed by an etching gas such as chlorine.

As the result, carbon precipitates as graphene **102** on a surface of the solid solution layer. This is because carbon is not able to remain dissolved due to decrease of the metal.

If etching is continued longer, the precipitated graphene **102** grows further. Since etching is carried out while maintaining a solid solution temperature, carbon that has not yet precipitated has mobility in the metal. Therefore, carbon that is not able to remain dissolved due to etching of the metal precipitates to form a crystal structure with the already precipitated graphene.

Finally, all the metal is removed and the graphene **102** comes to touch directly a surface of the substrate **103**.

In this way, different from a conventional thermal CVD method using a metal catalyst, graphene **102** is able to be formed directly on a substrate **103** in a condition not containing a metal. Further, by selecting the shape of a solid solution layer appropriately, a pattern of the graphene **102** finer than that by a conventional transcription technique of graphene produced by a thermal CVD method is able to be formed.

In this regard, in forming a solid solution layer by conducting heating with supplying a reducing agent, such as a mixture gas of hydrogen and argon, that is able to reduce a metallic oxide, the oxide is able to be prohibited from remaining on the substrate.

However, if an atmosphere not allowing oxidation of a metallic (for example, an atmosphere with adequately low partial pressure or concentration of an oxidizing agent) or vacuum is able to be maintained during formation of a solid solution layer, the supply of a reducing agent is not necessary.

A case, in which an etching gas with a constant concentration touches a surface of a solid solution layer and a metal is etched uniformly, will be considered.

In this case, if the concentration distribution of carbon in the solid solution layer is uniform, the initiation point of precipitation of graphene **102** on the surface of the solid solution layer becomes random.

On the other hand, if the concentration distribution of carbon in the solid solution layer is inhomogeneous, graphene **102** precipitates initially at a point with high carbon concentration and grows toward points with low carbon concentration.

Therefore, by setting appropriately the concentration distribution of carbon, the growth initiation position and the growing direction of a crystal of graphene **102** is able to be regulated.

Further, if the concentration distribution of an etching gas is able to be set inhomogeneous, a metal is removed faster at a position with high concentration of the etching gas. Therefore, even if the concentration distribution of carbon is uniform in the solid solution layer, graphene **102** precipitates

12

initially at a position with high concentration of the etching gas and grows toward a position with low concentration of the etching gas.

Accordingly, also by setting appropriately the concentration distribution of an etching gas, the growth initiation position and the growing direction of a crystal of graphene **102** is able to be regulated.

Therefore, if the initiation point and the direction of the growth of graphene are regulated, crystal grain boundaries of graphene are formed only at the growth initiation point and growth termination points, where graphene connects each other, the crystal grain boundaries are able to be regulated to predetermined positions, and an extremely large crystal grain size is able to be realized by reducing the growth initiation points of graphene.

Further by combining appropriately the above setting of the concentration distribution of carbon in a solid solution layer and the concentration distribution of an etching gas, it is possible that the growth initiation position and the growing direction of a crystal of graphene **102** be regulated.

In the above description, iron is used as a metal and chlorine is used as an etching gas. However, any metal that is able to dissolve carbon and an etching gas for the metal is able to be also used. Namely, by heating the metal and carbon on a substrate **103** to a solid solution temperature to dissolve carbon into the metal and form a solid solution layer, then continuing the heating an etching gas for the metal is supplied to remove the metal from the solid solution layer and to have graphene **102** precipitate and grow, so that a graphene device **101** with graphene **102** directly attached to a surface of the substrate **103** is able to be also produced.

As a metal to be used as a solvent of a solid solution as described above, a pure metal composed of a single metal element and an alloy composed of a plurality of metal elements are able to be used. However, it is possible that an alloy composed of a metal element and a semi-metallic element, an alloy composed of a metal element and a nonmetallic element, or the like be used as a solvent of a solid solution, insofar as carbon is able to be dissolved as a solvent, and the alloy is able to be removed by etching or the like.

The crystal grain size (mean value thereof) of graphene **102** in the growing direction along the substrate **103** becomes larger than the crystal grain sizes (mean values thereof) in any other directions (for example, the direction perpendicular to the substrate **103**, or a direction along the substrate **103** but crossing the growing direction).

While, with respect to a mode of "continuation of heating", the temperature for forming a solid solution layer and the temperature for etching is not necessarily be same. For example, once a solid solution layer is formed and metal removal by etching is initiated, it is possible that the temperature be lowered gradually and reach a temperature, at which a solid solution is not able to be formed any more, (or a temperature slightly higher than the above temperature), when etching is completed.

The production method will be described in detail below referring to FIG. 5A to FIG. 5O. The figures are cross-sectional views for illustrating a process for producing a graphene device **101**. While, the parameters listed below are just an example to facilitate understanding, and an embodiment with parameters appropriately replaced falls within the scope of the present invention.

As shown in FIG. 5A a substrate **103** is prepared as a basis for forming a prepared graphene device **101**. Although a silicon dioxide substrate is used as the substrate **103** in the present example, as described above, a multilayer substrate, a

13

substrate with various elements buried inside, a substrate to be provided with various elements on the rear surface, or the like is able to be also utilized.

As shown in FIG. 5B, a first mask **501** is formed on a surface of the substrate **103**. The first mask **501** defines a pattern shape of graphene **102** to be formed finally.

When a photolithographic technique with visible light or ultraviolet light is applied, a resist is coated on the substrate **103** and the shape of the first mask is exposed on the resist surface, followed by developing and dissolving of the resist to form the first mask **501**. Alternatively, it is possible that an electronic beam lithographic technique, or a technique, by which a mask made of a metal film provided with slits and holes is attached tightly, be applied.

The first mask **501** defines a pattern shape of graphene **102** in the finally produced graphene device **101**. Namely, graphene **102** is formed in an exposed region of a surface of the substrate **103** not masked by the first mask **501**.

Further, carbon is supplied by sputtering, vacuum deposition, CVD, or otherwise to form a carbon layer **502** as shown in FIG. 5C on a surface of the first mask **501** and through openings of the first mask **501** on an exposed surface of the substrate **103**. It is possible that the carbon layer **502** be amorphous or crystalline.

Although in the figure carbon is supplied uniformly and the carbon layer **502** with uniform thickness is formed, it is possible that carbon be supplied only near the openings of the first mask **501** to suppress formation of unnecessary carbon layer **502**.

Then by performing dissolution of the resist, the first mask **501** and the carbon layer **502** formed on the surface thereof are removed as shown in FIG. 5D to yield a carbon layer **502** having the same shape as the intended pattern as an initial layer (a layer having an initial shape to define a final pattern shape of graphene **102**).

Namely, naming of an initial layer means not 'a first formed layer' but "a layer, in which carbon to be used as a source material for graphene **102** is first contained".

Further, as shown in FIG. 5E, a second mask **503** is formed on the surface of the substrate **103** applying a similar technique as for the first mask **501**. In the present example, an opening of the second mask **503** has a shape including the entire opening of the first mask **501**, namely a shape same as or larger than the opening of the first mask **501**. In this way, the carbon layer **502** is positioned in the opening of the second mask **503**.

Then, a metal is supplied by sputtering, vacuum deposition, CVD, or otherwise to form a metallic layer **504** as shown in FIG. 5F on a surface of the second mask **503** and through openings of the second mask **503** on exposed surfaces of the carbon layer **502** and the substrate **103**.

In the figure, a metal is supplied not uniformly but nonuniformly, so that the thickness of the metallic layer **504** increases gradually and then returns to the original thickness cyclically forming a saw-toothed shape. By applying a mask vapor deposition method, the thickness of the metallic layer **504** is able to be changed as above.

In this regard, the mask vapor deposition method is specifically a technique as follows. Namely, by providing a metal foil or the like with a plurality of slits to form a self-supporting mask. Next, the self-supporting mask is placed with a certain distance from the substrate **103**, and then a metal is supplied by sputtering through the self-supporting mask up to the substrate **103**. In this case, in a zone facing a slit of the self-supporting mask a metallic layer **504** becomes thick, and with increased distance therefrom the metallic layer **504** becomes thinner.

14

Further, a plurality of wires placed touching the surface of the substrate **103** are able to substitute for the above self-supporting mask. In this case the wires constitute obstacles to sputtering and therefore the metallic layer **504** becomes thin in the vicinity of the wires, and with increased distance therefrom the metallic layer **504** becomes thick.

Further, there is a technique by which one or plural movable shutters are provided and the shutters are gradually shut, when a metal is supplied by sputtering. By the technique the metallic layer **504** near a part, where a shutter is first closed, becomes thin and the metallic layer **504** near a part, where a shutter is last closed, becomes thick.

In the present example, although the sputtering direction is oblique to the substrate **103**, and the saw-tooth shape of the metallic layer **504** from the top to the foot is asymmetric, the same from the top to the foot are able to be made symmetric by setting the sputtering direction vertical to a surface of the substrate **103** as described below in Example 7.

Then by performing dissolution of the resist, the second mask **503** as well as the metallic layer **504** formed on the surface thereof are removed as shown in FIG. 5G. As the result, the carbon layer **502** is covered by the metallic layer **504** on the surface of the substrate **103**.

Then, by heating to a solid solution temperature allowing carbon to dissolve in a metal, the carbon layer **502** dissolves in the metallic layer **504** to form a solid solution layer **505** as shown in FIG. 5H.

The thickness of the solid solution layer **505** is coupled with the thickness of the metallic layer **504** and increases at a constant gradient and returns to the original thickness cyclically.

Since the carbon layer **502** was uniform as described above, where the solid solution layer **505** is thick, the carbon concentration is low, and where the solid solution layer **505** is thin, the carbon concentration is high. In the figure, the carbon concentration is expressed by gradation.

If an etching gas is supplied, while maintaining a solid solution temperature, the metal in the solid solution layer **505** is removed gradually. Although it is possible that the etching speed occasionally vary depending on the composition of the solid solution layer **505**, as a general tendency, when an etching gas is supplied uniformly, a metal is removed at an approx similar speed irrespective of the thickness of the solid solution layer **505**.

If the supply of an etching gas is continued together with heating, a zone appears, where carbon is not able to remain dissolved in the solid solution layer **505** due to removal of a metal. In the solid solution layer **505**, where the thickness is small, the carbon concentration is high.

Therefore, as shown in FIG. 5I, at a place where the thickness is small carbon unable to remain dissolved precipitates on a surface of the solid solution layer **505** as graphene **102**. Namely, a place where the thickness is small, and the carbon concentration is high, forms a growth initiation position of the graphene **102**.

If the heating to a solid solution temperature and the supply of the etching gas are continued even after carbon precipitates as the graphene **102**, the graphene **102** grows while maintaining the crystal structure as shown in FIG. 5J, FIG. 5K, FIG. 5L, FIG. 5M, and FIG. 5N. The growing direction of the graphene **102** is a direction from a zone with a high carbon concentration to a zone with a low carbon concentration in the solid solution layer **505**, namely a direction along the concentration gradient. In the present example, the graphene **102** grows from a place with a small thickness of the solid solution layer **505** to a place with a large thickness, namely from a

15

place with a small thickness of the metallic layer **504** to a place with a large thickness, and from right to left in the figures.

By adjusting the partial pressure of an etching gas, the precipitation speed of the graphene **102** is able to be regulated. If the metal in the solid solution layer **505** is iron or the like, chlorine is able to be used as an etching gas, and the partial pressure of an etching gas is able to be adjusted by diluting chlorine to a desired concentration.

In this way, when all the metal is removed from the solid solution layer **505**, the graphene **102** touches directly the substrate **103** as shown in FIG. 50. In this way, the graphene device **101** is completed.

A zone, where the thickness of the solid solution layer **505** was large, becomes a zone, where the graphene **102** grown from right collides with left adjacent graphene **102**, and therefore a crystal grain boundary **104** appears from the surface of the graphene **102** to the surface of the substrate **103**.

Further, as a zone, where a crystal grain boundary **104** appears, a growth initiation position of the graphene **102** is conceivable, and more details will be described in Examples described below.

Various variations of a production method for a graphene device **101** will be described briefly below. The variations thereof will be described in more detail in the following Examples.

First of all, formation of a second mask **503** is not prerequisite. For example, after forming the carbon layer **502** and without removing the first mask **501**, it is possible that the metallic layer **504** be formed. Alternatively, after removing the first mask **501**, it is possible that the metallic layer **504** be immediately formed covering the surfaces of the substrate **103** and the carbon layer **502**.

If graphene **102** is to be formed on the entire surface of the substrate **103**, the first mask **501** or the second mask **503** is not required to be formed. After the carbon layer **502** is formed over the entire surface of the substrate **103**, the metallic layer **504** should be formed thereon.

Although in the above mode the carbon layer **502** and the metallic layer **504** are formed in separate stages, it is possible that a mixture of a carbon and a metal be supplied after the first mask **501** is formed. In this case, by removing the first mask **501** a mixture layer having the same shape with the desired pattern is obtained as an initial layer.

For forming such a mixture layer a co-deposition technique of a metal and carbon is able to be adopted. For example, sputtering is performed using simultaneously 2 targets, the one composed of a metal and the other composed of carbon. Alternatively, when sputtering is performed using a single target, it is possible that a target of a mixture of carbon and iron be used, or it is possible that sputtering be performed using a target composed of iron attached with a carbon chip, or it is possible that sputtering be performed using a target composed of carbon attached with an iron chip. In the mode using an attached chip, by adjusting the number of attached chips, the carbon concentration in a mixture layer as an initial layer is able to be easily adjusted.

It is possible that the order of formation of a carbon layer **502** and a metallic layer **504** be exchanged. Namely, a technique that the metallic layer **504** is formed on the substrate **103** and then the carbon layer **502** is formed on the metallic layer **504**, is possible. In this case the carbon layer **502** corresponds to an initial layer.

Moreover there is a technique as below, by which the pattern shape of an initial layer is formed without utilizing the first mask **501** or the second mask **503**. Namely, according to the technique,

16

(a) the carbon layer **502** and the metallic layer **504** are formed, or

(b) a mixture layer of carbon and a metal is formed, covering the surface of the substrate **103**, and thereafter the metal and carbon are etched to form the pattern shape of an initial layer.

According to the technique, after the formation by (a) or (b), a third mask is formed. With respect to the third mask, the opening thereof corresponds to the masking part of the first mask **501**, and the masking part corresponds to the opening of the first mask **501**, and therefore the first mask **501** and the third mask constitute, a sort of, negative-positive relationship.

Then, etching is performed through the third mask for removing a metal and carbon in the openings of the third mask to form the pattern shape of an initial layer. Finally, the third mask is removed by etching. Thus, a metal and carbon are able to be formed to a desired pattern shape.

For forming a desired shape of an initial layer, there are various applicable pattern forming techniques in addition to the above. Consequently, carbon or a mixture of carbon and a metal, or the like is able to be used as a material for an initial layer. Further, as a developing solution for lithography, a material or a dissolving liquid for a resist, an etching agent, or the like, various materials are able to be used.

Further, if randomly generated crystals of graphene **102** are acceptable, it is not necessary to change the thickness of a metallic layer **504**, and it is possible to be designed uniform.

Alternatively, if a crystal of graphene **102** is to be enlarged for forming a uniform continuous film, it should be so arranged that the concentration gradient of carbon is oriented to the same direction to the extent possible at any positions. A technique for obtaining a larger single crystal of graphene **102** will be described in the following Example.

According to the above mode the thickness of the carbon layer **502** is made uniform, on the other hand the supplied quantity of a metal is made inhomogeneous in terms of a position so as to change the thickness of the metallic layer **504** and to generate a gradient of the carbon concentration in the solid solution layer **505**. However, for example, by making the supply quantity of carbon inhomogeneous in terms of the positions, or by changing the supply quantities of a metal and carbon in terms of the positions, it is possible that a gradient of the carbon concentration be generated to determine a growing direction of graphene **102**.

Further, according to the above mode, by making the concentration distribution of an etching gas uniform, removal of a metal is carried out at a constant rate at any positions of the solid solution layer **505**. However, by making the concentration distribution of an etching gas inhomogeneous, the speed of metal removal is able to be changed depending on the positions. Consequently, it is possible to design for causing precipitation of graphene **102** from a place with a higher concentration of an etching gas to a place with a lower concentration.

Example 3

According to the present embodiment, by applying the above embodiments in multi-stages, the size of a single crystal of the graphene **102** is adjusted, and the positions of crystal grain boundaries are defined, which is suitable, for example, for producing a graphene device **101** as shown in FIG. 2.

By a production method according to the present embodiment, line-shaped graphene is grown in the first direction on the substrate **103** using the production method for graphene of Example 2.

17

FIG. 6A is a plan view illustrating line-shaped graphene and the growing direction thereof. The example will be described below referring to the figure.

In the example shown in the figure a large number of pieces of line-shaped graphene **601** divided by crystal grain boundaries **104** grow from the respective grid points on the substrate **103** toward the upward adjacent grid points.

To form such line-shaped graphene **601**, the first mask **501** for the carbon layer **502**, having openings in a form of an array of straight lines in a vertical direction at regular intervals, is used. As for the thickness of the metallic layer **504**, such a pattern that the thickness increases gradually upward and then returns suddenly to the original thickness cyclically, is applied.

Next, using the production method for graphene in Example 2, a carbon layer **502** and a metallic layer **504** are formed in a region on the surface of the substrate **103**, where the line-shaped graphene **601** has not been formed, and then planar graphene is allowed to grow in the second direction.

FIG. 6B is a plan view illustrating planar graphene and the growing direction thereof. The example will be described below referring to the figure.

The figure depicts a process in which planar graphene **602** grows from the respective pieces of line-shaped graphene **601** as initiation lines from right to left.

In order to grow the planar graphene **602** as in the present mode, the first mask **501** for the carbon layer **502** and the second mask **503** for the metallic layer **504** having openings corresponding to regions where the line-shaped graphene **601** is not formed are able to be used, or it is possible that the use of the first mask **501** or the second mask **503** be omitted.

As for the thickness of the metallic layer **504**, such a cyclic pattern that the thickness increases gradually from the respective line-shaped graphene **601** toward the leftward adjacent line-shaped graphene **601** is applied.

In this case, the already formed line-shaped graphene **601** becomes a seed for forming a crystal of the planar graphene **602** (in FIG. 6B, 2-dotted broken lines indicate the border-lines where the line-shaped graphene **601** was located.).

By such an arrangement, the growing direction of the planar graphene **602** becomes from right to left.

This figure depicts the growth of the planar graphene **602** on the halfway, and the growth continues until the front edge of the planar graphene **602** finally reaches an adjacent planar graphene **602** (where the line-shaped graphene **601** was located before).

By forming the graphene **102** as above, a graphene device **101** with single crystals arranged in a grid pattern as illustrated in FIG. 2, in which line segments connecting adjacent grid points constitute crystal grain boundaries, is able to be produced.

In this case, the smaller the dimension of the grid square is, the shorter the production time for covering the substrate **103** becomes, although the dimension of the crystal of the graphene **102** becomes also smaller. Therefore it is possible that the dimension and the number of the grid squares be selected appropriately according to the end use or the production cost.

In the case only one line-shaped graphene **601** is formed from the lower edge to the upper edge of the substrate **103** and planar graphene **602** is grown from the line-shaped graphene **601** to the opposite edge of the substrate **103** facing to the line-shaped graphene **601**, it is also possible to form a single crystal of graphene **102** covering the entire substrate **103**.

In the following the variations of the production method described in the Example 2 will be described one by one. In

18

the following descriptions, with respect to similar elements as in the above modes, descriptions are omitted appropriately to facilitate understanding

Example 4

The present embodiment is a production method for a graphene device **101** forming the graphene **102** on the entire surface of the substrate **103**.

According to the present embodiment a graphene device **101** as shown in FIG. 1A and FIG. 1B is able to be produced. FIG. 7A to FIG. 7F are diagrams illustrating a process of the production method for the graphene device **101** according to the present embodiment. The example will be described below referring to the figures.

According to the present production method, the substrate **103** is prepared first of all (FIG. 7A).

Then the carbon layer **502** is formed on the surface of the substrate **103** (FIG. 7B), and further the metallic layer **504** is formed (FIG. 7C). As described above, it is possible that the order of formation of the carbon layer **502** and the metallic layer **504** be reversed, or it is possible that a mixture layer be formed by means of sputtering, vapor deposition, CVD, or the like of a mixture of carbon and a metal.

Thereafter, by conducting heating up to a solid solution temperature, the solid solution layer **505** dissolving carbon in a metal is formed (FIG. 7D).

Further, a metal is etched from the solid solution layer **505** by supplying an etching gas, while continuing the heating, so that graphene **102** precipitate on the surface of the solid solution layer **505** and starts growing (FIG. 7E).

When all the metal is etched, a graphene device **101**, in which the graphene **102** touches directly the surface of the substrate **103**, is completed (FIG. 7F).

Example 5

This embodiment is a production method for a graphene device **101** without using the second mask **503**. By this technique, for example, a graphene device **101** having a pattern as shown in FIG. 3 is able to be produced.

FIG. 8A to FIG. 8H are diagrams illustrating a process of a production method for a graphene device **101** according to the present embodiment. The example will be described below referring to the figures.

According to the present production method, the substrate **103** is prepared first of all (FIG. 8A).

Next, the first mask **501** is formed on the surface of the substrate **103** (FIG. 8B). Thereafter, a carbon layer **502** is formed (FIG. 8C), and further a metallic layer **504** is formed (FIG. 8D).

Then, by dissolving the first mask **501**, the carbon layer **502** and the metallic layer **504** on the first mask **501** are removed (FIG. 8E).

After the formation of the carbon layer **502**, it is possible that the first mask **501** and the carbon layer **502** be first removed, and then the metallic layer **504** is formed and it is possible that the following treatments be followed.

After the carbon layer **502** is formed to the same shape as a desired pattern shape by removal, heating to a solid solution temperature is conducted to form a solid solution layer **505** dissolving carbon in a metal (FIG. 8F).

Further, a metal is etched from the solid solution layer **505** by supplying an etching gas, while keeping a solid solution temperature, so that graphene **102** precipitate on the surface of the solid solution layer **505** and starts growing (FIG. 8G).

19

When all the metal is etched, a graphene device **101**, in which the graphene **102** touches directly the surface of the substrate **103**, is completed (FIG. **8H**).

Example 6

This embodiment is a production method for a graphene device **101** without using the first mask **501** and the second mask **503**. By this technique, for example, a graphene device **101** having a pattern as shown in FIG. **3** is able to be produced.

FIG. **9A** to FIG. **9I** are diagrams illustrating a process of a production method for a graphene device **101** according to the present embodiment. The example will be described below referring to the figures.

According to the present production method, the substrate **103** is prepared first of all (FIG. **9A**).

Next, the carbon layer **502** is formed on the surface of the substrate **103** (FIG. **9B**), and further the metallic layer **504** is formed (FIG. **9C**).

Then, a third mask **801** is formed on the metallic layer **504** (FIG. **9D**). The third mask **801** is a mask in a negative-positive relationship with the first mask **501**.

Thereafter, from the openings of the third mask **801** (exposed parts of the metallic layer **504**) unnecessary parts of the metallic layer **504** and the carbon layer **502** are removed (FIG. **9E**). For removing the metallic layer **504**, plasma etching using a gas containing a halogen, or the like is able to be applied. For removing the carbon layer **502**, plasma ashing using a gas containing oxygen, or the like is able to be applied.

Further, the third mask **801** is removed (FIG. **9F**).

Thereafter, similarly as in the above embodiment, heating to a solid solution temperature is conducted to form a solid solution layer **505** dissolving carbon in a metal (FIG. **9G**).

Further, a metal is etched from the solid solution layer **505** by supplying an etching gas, while continuing the heating, so that graphene **102** precipitate on the surface of the solid solution layer **505** and starts growing (FIG. **9H**).

When all the metal is etched, a graphene device **101**, in which the graphene **102** touches directly the surface of the substrate **103**, is completed (FIG. **9I**).

Example 7

This embodiment is a production method for a graphene device **101** by allowing graphene **102** to grow out of the solid solution layer **505** formed in the Examples 4, 5 or 6 from a desired position in a desired direction.

FIG. **10A** to FIG. **10E** are diagrams illustrating a process of a production method for a graphene device **101** according to the present embodiment. The example will be described below referring to the figures.

According to the present production method, 2 sheets of substrates **103** on which the carbon layer **502** and the metallic layer **504** are formed as in FIG. **7C**, FIG. **8E**, and FIG. **9F** are prepared and placed facing each other (FIG. **10A**).

When heated to a solid solution temperature, solid solution layers **505** facing each other are formed on the substrates **103** facing each other similarly as in FIG. **7D**, FIG. **8F**, and FIG. **9G** (FIG. **10B**).

Thereafter, an etching gas is supplied from both ends of the substrates **103**. In this case, a metal is removed faster at the edge parts of the solid solution layers **505** than the central parts of the solid solution layers **505**. In other words, graphene **102** precipitates first at the edge parts of both the substrates **103** and the graphene **102** grows toward the central parts (FIG. **10C** and FIG. **10D**).

20

When all the metal is etched, a graphene device **101**, in which the graphene **102** touches directly the surface of the substrate **103**, is completed (FIG. **10E**). In this graphene **102**, crystal grain boundaries **104** appear at the central parts.

It is possible that the etching gas be supplied only from an end. In this case, the graphene **102** grows from the edge parts in the supply direction of the etching gas (flow direction or diffusion direction of the etching gas).

Example 8

This Example is a production method for a graphene device **101**, by forming the carbon layer **502** as in the Examples 4, 5 and 6, thereafter forming the thickness of the metallic layer **504** inhomogeneous, and allowing graphene **102** to grow from a desired position in a desired direction.

According to the present embodiment, the substrate **103**, on which a carbon layer **502** is formed, is prepared (FIG. **11A**).

Then a self-supporting mask **901** (for example, a metal foil or the like provided with slits **902**) is placed with a certain distance from the substrate **103** and the carbon layer **502**, and a metal is supplied through the slits by vapor deposition, sputtering, CVD, or the like (FIG. **11B**).

By doing so, a metallic layer **504** is formed thick in the vicinity of the slits **902**, and with increased distance from the slits **902** the metallic layer **504** becomes thinner.

Although in Example 2, by regulating the sputtering direction in supplying a metal, the metallic layer **504** is formed to have a cross-section in a saw-toothed shape, in the present figure a metal is supplied from top to bottom and therefore the shape of the metallic layer **504** becomes bilaterally symmetrical.

If the present technique is applied to Example 4, the carbon layer **502** (and also the metallic layer **504**) takes a desired shape at this stage.

If the present technique is applied to Example 5, after forming the metallic layer **504**, the first mask **501** is detached and the carbon layer **502** (and also the metallic layer **504**) is formed into a desired pattern shape.

If the present technique is applied to Example 6, thereafter the third mask **801** is formed, unnecessary parts of the carbon layer **502** and the metallic layer **504** are detached, and the third mask **801** is dissolved to form the carbon layer **502** (and also the metallic layer **504**) into a desired pattern shape.

While, as described above, in the case the metallic layer **504** is formed by the present technique after the carbon layer **502** is formed in a desired pattern shape, it is not required to form the metallic layer **504** in a desired pattern shape.

Thereafter, by conducting heating up to a solid solution temperature to form the solid solution layer **505** (FIG. **11C**), and by supplying an etching gas, while continuing the heating, to remove a metal from the solid solution layer **505**, graphene **102** precipitates at zones where the metallic layer **504** was thin and grows toward zones where the metallic layer **504** was thick (namely in the figures laterally) (FIGS. **11D**, **E** and **F**).

When all the metal is etched, a graphene device **101**, in which the graphene **102** touches directly the surface of the substrate **103**, is completed (FIG. **11G**). In the example shown in the figures, at a central part, where the growing directions collide each other, crystal grain boundaries **104** of the graphene **102** appear. It is possible that the crystal grain boundaries **104** of the graphene **102** occasionally appear at growth initiation points.

Example 9

This Example is a production method, by which, in repeating Example 8 twice, the pattern shape of the carbon layer **502**

21

is changed, and the direction of the self-supporting mask **901** is rotated by 90°, for producing a graphene device **101** having crystal grain boundaries **104** in a grid form as shown in FIG. 2.

FIG. 12A to FIG. 12F are plan views illustrating the position relationship according to the present embodiment among the carbon layer **502**, the self-supporting mask **901**, and the like. The example will be described below referring to the figures.

According to the present production method, a pattern of the carbon layer **502** is first formed on the surface of the substrate **103** as if parallel lines are drawn (FIG. 12A). In the figure, the pattern of the carbon layer **502** extends vertically.

Then, based on the technique of Example 8, the self-supporting mask **901** is placed such that the slits **902** cross the pattern of the carbon layer **502** (FIG. 12B). Although, the self-supporting mask **901** is depicted smaller than the substrate **103** or the carbon layer **502** in the figure to facilitate understanding, the actual size is larger than them and the slits **902** are placed regularly and cyclically.

Then, a metal is supplied to form a metallic layer **504**. In this case the thickness of the metallic layer **504** varies along the vertical direction of the figure.

By heating them the solid solution layer **505** is formed, and the metal is removed by etching. Then, the graphene **102** grows in a direction orthogonal to the longitudinal direction of the slit **902** of the self-supporting mask **901**, namely vertically in the figure.

When the metal is removed totally, line-shaped graphene **601** is formed (FIG. 12C).

Thereafter, a pattern of the carbon layer **502** is formed on the substrate **103** outside the zones of line-shaped graphene **601** (FIG. 12D).

Then, based on the technique of Example 8, the self-supporting mask **901** is placed such that the slits **902** are parallel to the longitudinal direction of the line-shaped graphene **601**, and the slits **902** are placed at the middle between two adjacent line-shaped graphene **601** (FIG. 12E).

Although, the self-supporting mask **901** is depicted smaller than the substrate **103** or the carbon layer **502** in the figure to facilitate understanding, the actual size is larger than them and the slits **902** are placed regularly and cyclically.

Then, a metal is supplied to form a metallic layer **504**. In this case the thickness of the metallic layer **504** varies along the horizontal direction of the figure.

In this regard, in order to prevent formation of a metallic layer **504** on the line-shaped graphene **601**, it is possible that a mask or the like be utilized appropriately. Further, it is possible to be so constituted that a part of the line-shaped graphene **601** is able to remain without dissolving in the metallic layer **504**, by adjusting the supplied quantity of the metal, the size of the slits **902** of the self-supporting mask **901**, or the distance to the substrate **103**.

Then, by heating them the solid solution layer **505** is formed, and the metal is removed by etching.

Then, planar graphene **602** grows from the line-shaped graphene **601** that has remained without dissolving in the solid solution layer **505** as the initiation position in a direction orthogonal to the longitudinal direction of the slit **902** of the self-supporting mask **901**, namely perpendicular to the longitudinal direction of the line-shaped graphene **601**, and horizontally in the figure.

When the metal is removed totally, planar graphene **602** divided by crystal grain boundaries **104** in a grid form is formed (FIG. 12F).

Example 10

Experimental examples with various parameters with respect to the respective modes above, and experimental

22

results with respect to characteristics of graphene devices to be yielded according to the parameters, will be described below.

EXPERIMENT 1

In Experiment 1 specific parameters with respect to the technique of Example 4 were examined.

As the substrate **103**, a silicon substrate with a thermally oxidized film with the thickness of 1000 nanometers was adopted.

According to the parameters, an amorphous carbon layer **502** with the thickness of 40 nanometers was formed by sputtering. A metallic layer **504** made of iron with the thickness of 83 nanometers is formed thereon by sputtering.

They were placed in a reactor; then the reactor was evacuated to vacuum, and, flowing a mixture gas of hydrogen and argon (hydrogen content: 40 vol-%) at a total pressure of 5 Torr, heated up to a solid solution temperature range (600° C. to 1000° C., a typical solid solution temperature is 800° C.); the temperature was maintained for 10 min; and annealing was conducted to form a solid solution layer **505**.

Thereafter, keeping the heating at a solid solution temperature, the supplied gas was switched to a mixture gas of chlorine and argon (chlorine content: 0.01 vol-%) and flown at a total pressure of 5 Torr for 30 min for etching a metal.

After the completion of metal removal, the heating was terminated to cool down the reactor, and the graphene **102** formed on the surface of the substrate **103** was analyzed.

Under the parameters, the average film thickness of the solid solution layer **505** was decreased at a constant rate with elapsed time, and the etching rate was 21 nanometers per min.

If a metallic layer **504** alone is etched under similar conditions, the etching rate is almost same as a solid solution layer **505**, but if a carbon layer **502** alone is etched under similar conditions, the thickness of the carbon layer **502** does not change.

In other words, if an etching gas is supplied keeping the heating at a solid solution temperature, a metal is able to be removed preferentially from the solid solution layer **505**.

By Raman scattering spectroscopy, from a G-band originated from a crystal structure, a D-band originated from an amorphous structure, and a G'-band originated from graphene, as well as intensities thereof, it is able to be estimated to what extent amorphous carbon is converted to crystalline graphene **102**, or what is an approximate layer number of the graphene **102**.

FIG. 13A is a graph showing a Raman spectrum in the event a solid solution layer **505** is formed and then quenched without etching, and FIG. 13B is a graph showing a Raman spectrum in the event a production method with the parameters according to the present embodiment is used. The example will be described below referring to the figures.

The abscissa of the graphs shown in the figures represents Raman shift from 1000 cm⁻¹ to 3000 cm⁻¹, and the ordinate represents intensity of the spectrum.

In FIG. 13A corresponding to a conventional technique, besides G-band and D-band, peaks of amorphous carbon appear over a broad range between the two bands.

On the other hand, in FIG. 13B according to the present invention, G-band originated from a crystal structure becomes sharp and high, and D-band originated from defects becomes small. Further, peaks of amorphous carbon between the two bands are remarkably reduced.

Further, G'-band originated from graphene in the graphene **102** becomes also sharp and high.

23

Further, by fluorescent X-ray analysis, a metal is below the detection limit, while it became clear that the thickness of the graphene **102** was 19 nanometers.

On the other hand, according to a conventional technique corresponding to FIG. 13A, a large amount of iron corresponding to the thickness of 83 nanometers remains under low-crystallinity graphene.

Consequently, in contrast to a conventional technique, by the technique according to the present invention, it is clear that high-crystallinity high purity graphene **102** not containing a catalyst metal is obtained touching directly the silicon substrate **103** with a thermally oxidized film.

EXPERIMENT 2

Following Experiment 1, specific parameters were further examined in Experiment 2.

Namely, in order to form a solid solution layer **505** dissolving carbon in iron, a carbon layer **502** with the thickness of 113 nanometers was formed firstly, and a metallic layer **504** was formed thereon, followed by heating. With respect to such a mode, change of the characteristics of the graphene **10** depending on the thickness of the metallic layer **504** was examined. As the thickness of the metallic layer **504**, 4 values of 83 nanometers, 132 nanometers, 233 nanometers, and 393 nanometers were applied.

FIG. 14 is graphs showing features of Raman spectra for metallic layers with various thicknesses, which are cooled after annealing, after etching for 3 min, and after etching for 30 min. The example will be described below referring to the figure.

The abscissa of the respective graphs shown in the figure represents, similarly as in FIGS. 13A and 13B, Raman shift from 1000 cm^{-1} to 3000 cm^{-1} , and the ordinate represents intensity of the spectrum.

As shown in the figure, with respect to the metallic layer **504** with the thickness of 393 nanometers, by annealing only carbon does not precipitate onto the surface and a peak originated from graphene is almost absent, but with the progress of etching precipitation of graphene advances.

With respect to the condition of the metallic layer **504** with the thickness of 233 nanometers, 132 nanometers, or 83 nanometers, a multilayer graphene layer is already precipitated after annealing.

With respect to the metallic layer **504** with the thickness of 233 nanometers, 3 min after the etching the best spectrum is obtained.

On the other hand, with respect to the metallic layer **504** with the thickness of 132 nanometers or 83 nanometers, longer etching does not change the spectrum. This is conceivably because with a small thickness of the metallic layer **504** an amount of dissolved carbon is limited and therefore an amount that precipitates by etching is also limited.

Surfaces of the samples were observed by a scanning electron microscope to find that between after annealing and after etching for 3 min, there was little change in terms of the surface smoothness and the number of voids irrespective of the thickness of the metallic layer **504**, but after etching for 30 min the surface roughness and the number of voids increased.

With respect to the metallic layer **504** with the thickness of 393 nanometers, after the completion of etching for 30 min the film of graphene **102** becomes discontinuous, and it was the metallic layer **504** with the thickness of 233 nanometers that had the least number of voids and the largest size of crystal.

24

From the experiments it is expected that the thickness of a metallic layer **504** made of iron is preferably approx. 1.0-fold to 2.5-fold that of a carbon layer **502**, if etching is conducted at 800°C .

While, there is a breadth for a solid solution temperature from the lower limit to the upper limit, and moreover it varies by the carbon concentration in a metal or a metal type. Therefore, it is possible to change the heating temperature in etching. It is conceivable that, if the temperature in etching is set high, a preferable thickness of a metallic layer **504** is smaller, and if the temperature is etching is set low, a preferable thickness of a metallic layer **504** is larger.

EXPERIMENT 3

In Experiment 3 specific parameters with respect to Examples 5 and 6 were examined.

As the substrate **103** a silicon substrate with an oxidized film was adopted, the first mask **501** was formed by ultraviolet light lithography, the carbon layer **502** and the metallic layer **504** were coated thereon by sputtering, and a resist of the first mask **501** was removed to produce an initial layer pattern with the line width of $2\text{ }\mu\text{m}$.

The thickness of the carbon layer **502** was made 33 nanometers, and for the metallic layer **504** two kinds of 68 nanometers (parameters A), and 39 nanometers (parameters B) were prepared.

Setting other parameters as in the above Experiments, the graphene **102** was formed on the substrate **103**.

FIG. 15A is a diagram showing an atomic force microscope image of patterned graphene **102** produced according to parameters A. FIG. 15B is a diagram showing an atomic force microscope image of patterned graphene **102** produced according to parameters B. The example will be described below referring to the figures.

As obvious from the figures, parameters A give higher roughness compared to parameters B. While, the resistivity at the core part in the case of parameters A was $4 \times 10^{-3}\text{ }\Omega\text{cm}$, and in the case of parameters B was $6 \times 10^{-3}\text{ }\Omega\text{cm}$.

Namely, in the case of parameters A, since the metallic layer **504** is thick, the crystallinity is high and the resistance is low, but the roughness is high.

On the other hand, in the case of parameters B, although the resistance is slightly high but the smoothness is good. Consequently, the structure and the electrical conductivity were further examined for the case of parameters B.

FIG. 16A is an enlarged view showing an atomic force microscope image of patterned graphene **102** produced according to the parameters B, and FIG. 16B is a diagram showing an electrical current map of the patterned graphene **102** produced according to the parameters B. The example will be described below referring to the figures.

From the figures it becomes clear that at a region with a flat line the electrical conductivity is superior, and at a raised region or a depressed region the electrical conductivity is low. Conceivably, this is because the graphene according to the present production method is formed vertical to the substrate surface by c-axis orientation, and if a probe is placed at a raised region, the current flows first through a path in a c-axis direction with high resistance then to a flat region.

Example 11

In the Example 3, graphene is grown in a direction linearly, and thereafter the same is grown in the direction orthogonal to the line, namely in the direction for broadening the width of the line to form planar graphene.

25

According to the present embodiment, a graphene device having planar graphene is formed by a simpler technique.

FIG. 17 is a diagram illustrating a process of a production direction for a graphene device according to the present embodiment. The example will be described below referring to the figure.

In the figure a step is illustrated, in which the metallic layer 504 is formed on the carbon layer 502 (hidden in the figure) with uniform thickness already formed on the substrate 103.

The metallic layer 504 is depicted in the figure with shading, and a region with darker shading indicates that the metallic layer 504 is thinner there, and a region with lighter shading indicates that the metallic layer 504 is thicker there.

The metallic layer 504 according to the present embodiment is formed to a grid. Each grid square has a shape, of which a tiny square constituting the first region is connected with the left lower apex of a large square constituting the second region.

The thickness of the metallic layer 504 is thinner in the first region than in the second region, and there is a gradient in the second region increasing from the left lower apex toward 3 other apexes.

With such a constitution, the heating is conducted as the above embodiments to dissolve the carbon layer 502 in the metallic layer 504. As the result, the carbon concentration at a zone with dark shading in the figure becomes high, and the carbon concentration at a zone with light shading becomes low.

Consequently, when a metal is removed under conducting the heating, graphene precipitates first in the first region, namely near the left lower apex of the grid square. The graphene precipitated there is in general polycrystalline.

If the heating and the removal of a metal are continued, polycrystalline grains are confined to any one as a crystal nucleus by a constriction (bottleneck) near the left lower apex of the grid square. Consequently, the width of the constriction is made sufficiently smaller than a typical magnitude of the particle diameter of a polycrystalline grain to be precipitated by such a construction method. In this way, graphene precipitated at a part of the second region touching the constriction becomes a single crystal.

According to this invention, carbon grows from the single crystal as a nucleus toward 3 other apexes in the second region, namely spreads in the upper right direction.

In this case, since the crystal nucleus of growing carbon is confined by a constriction, any of grid patterned planar graphene obtained in the end becomes a single crystal.

While, the shapes of the first region and the second region are not necessarily limited to square, but are able to take any shape. For example, if the second region takes a shape that is able to fill a plane, such as rectangle and regular hexagon, a large number of large planar graphene with the same shape is able to be formed simultaneously. Meanwhile, it is possible that the first region take any shape, insofar as a constriction is formed, and for example it is possible to adopt a round shape besides square.

Example 12

This Example attempts no active control on the growing direction of graphene, and corresponds to a simplified technique of the above Examples. Experiment results of a mode, in which the thickness of the carbon layer 502 and the thickness of the metallic layer 504 are formed constant respectively, and a mode, in which a mixture layer containing carbon

26

and a metal mixed homogeneously is formed as an initial layer and formation of a metallic layer 504 is omitted, will be described below.

EXPERIMENT 4

In this Experiment formation of graphene 102 was compared under various conditions by exchanging the order of formation of a carbon layer 502 as an initial layer and a metallic layer 504. In this connection, the thickness of the metallic layer 504 was made constant in this Experiment.

In this Experiment, Raman spectrum was examined for each case of:

- (a) The thickness of the carbon layer 502: 113 nm;
- (b) The thickness of the metallic layer 504 composed of iron: 83 nm, 132 nm, 233 nm, and 393 nm; and
- (c) With annealing only, and with etching for 3 min

FIG. 18 is graphs showing features of Raman spectra in the event a carbon layer 502 is formed on a metallic layer 504 and cooled after annealing, and after etching for 3 min. The example will be described below referring to the figure. The abscissa of the respective graphs shown in the figure represents, similarly as in FIGS. 13A, 13B and 14, Raman shift from 1000 cm^{-1} to 3000 cm^{-1} , and the ordinate represents intensity of the spectra.

As shown in the figure, if the metallic layer 504 is as thick as 393 nm, immediately after the annealing only a peak originated from noise is visible, and graphene 102 is not formed, but it is clear that by conducting the etching for 3 min graphene 102 with high crystallinity is able to be formed.

However, under other conditions, immediately after the annealing a peak indicating low crystallinity (the left-end peak of 3 peaks) appears. With the progress of etching the crystallinity is improved.

Compared to FIG. 14, by various conditions, such as the order of formation of the carbon layer 502 and the metallic layer 504, the thickness to be formed, and etching time, the crystallinity of the obtained graphene varies.

Consequently, by selecting experimentally the best combination considering the time required for production or the source material cost, graphene with high crystallinity is able to be obtained.

In this Experiment, the carbon concentration in the solid solution layer 505 is substantially constant and therefore active control on the growing direction of the graphene is not performed.

Therefore, if the growing direction of the graphene is controlled by means of, for example, providing a gradient in the thickness of the metallic layer 504 as disclosed in the above Examples, the crystallinity is able to be further improved.

EXPERIMENT 5

In this Experiment a mixture layer of carbon and iron was formed by co-depositing carbon and iron and forming a film simultaneously, and used as an initial layer. Then, without forming a metallic layer 504 heating was conducted to form a solid solution layer 505, and the metal was removed by etching. The parameters for the Experiment were as follows.

A mixture layer of iron and carbon was deposited on a silicon oxide/silicon substrate by sputtering to the thickness of 25 nm to 35 nm.

Thereafter heating was conducted in a quartz glass tube at 500°C ., 600°C . and 700°C ., then keeping the temperature a mixture gas of chlorine and argon (chlorine as a corrosive agent: 0.01 to 0.05 vol-%) was circulated under reduced pressure for etching.

27

FIG. 19 is graphs showing features of Raman spectra corresponding to heating temperatures. The example will be described below referring to the figure.

As shown in the figure there are 3 peaks in each graph. Comparing the peaks, at 600° C. the central peak originated from a graphite structure is high and the right peak indicating generation of graphene also appears, however, the left peak indicating a defect is low. Therefore, the heating temperature was set at 600° C.

Further from an electron micrograph it became clear that particulate iron oxide was formed on the surface of the graphene 102.

Therefore, in forming the solid solution layer 505 by heating the mixture layer at 600° C., a mixture gas of hydrogen and argon (hydrogen: 25 vol-%) was circulated at 100 Torr for reducing iron oxide, followed by etching.

FIG. 20 is a graph showing features of a Raman spectrum of a sample prepared by a mode performing reduction of a metal oxide in forming a solid solution layer. The example will be described below referring to the figure.

As shown in the figure, according to the parameters the right peak indicating formation of graphene is larger, which indicates that graphene with high crystallinity is formed.

Although in this Experiment, the carbon concentration in the solid solution layer 505 was substantially constant and therefore active control on the growing direction of the graphene was not performed, high crystallinity was resulted.

Therefore, if the growing direction of the graphene is controlled by means of, for example, forming the metallic layer 504 provided with a gradient in the thickness as disclosed in the above Examples, the crystallinity is able to be further improved.

In this regard, in any of the above Examples, it is possible to refrain from intentional control on the growing direction of graphene, by omitting the formation of the metallic layer 504,

With respect to a treatment process, in which the solid solution layer 505 is formed by heating a co-deposited film (thickness 35 nm) of iron and carbon, and the film is then etched by chlorine, influence of the change in a hydrogen partial pressure during the heating is described below. The hydrogen functions therein as a reducing agent.

FIG. 21 is a scanning electron microscope picture showing final features of a graphene crystal when the hydrogen partial pressure is 1 Torr. FIG. 22 is a scanning electron microscope picture showing final features of a graphene crystal when the hydrogen partial pressure is 20 Torr. The example will be described below referring to the figures.

In FIG. 21,

- (a) at a right upper position, a large region surrounded by black and white duplex rims;
 - (b) at a right middle position, a white bright point surrounded by a black rim; and
 - (c) at a right slightly lower position, a white bright point surrounded by a black rim;
- and additionally small white bright points are imaged. They are particles of iron oxide.

In FIG. 22 such a bright point is not recognized at all, which indicates that the crystal shape of graphene is better than in the Example shown in FIG. 21.

The figures show that reduction with the heating in forming the solid solution layer 505 is effective.

Since the carbon concentration in the solid solution layer 505 is increased substantially uniformly due to etching of a metal, graphene nucleates at a random position. Since etching is performed keeping the heating, carbon holds high mobility and is able to diffuse over long distance. Therefore, by such a mode, carbon is incorporated by the firstly nucleated

28

graphene, new nucleation of graphene is suppressed, and graphene 102 with relatively large crystal grain size is able to be obtained. Further, in any of the above Examples a silicon substrate with thermally oxidized film is able to be adopted as the substrate 103, and graphene 102 is able to be formed directly without remaining a metal on the substrate 103.

This application claims priority based on Japanese Patent Application No. 2011-042781 filed on 28 Feb. 2011, the entire disclosure of which is incorporated by reference herein as far as the national law of the designated State permits.

INDUSTRIAL APPLICABILITY

According to the present invention, a production method for graphene, graphene produced on a substrate, and graphene on a substrate are able to be provided.

REFERENCE SIGNS LIST

- 101 Graphene device
- 102 Graphene
- 103 Substrate
- 104 Crystal grain boundary
- 401 Source electrode
- 402 Drain electrode
- 403 Insulator
- 404 Gate electrode
- 501 First mask
- 502 Carbon layer
- 503 Second mask
- 504 Metallic layer
- 505 Solid solution layer
- 601 Line-shaped graphene
- 602 Planar graphene
- 801 Third mask
- 901 Self-supporting mask
- 902 Slit

The invention claimed is:

1. A production method for graphene comprising:

- a forming step for forming a solid solution layer on a substrate, the solid solution layer comprising a metal in a solid state dissolving carbon, by heating to a solid solution temperature; and
- a removing step for growing the graphene made out of carbon precipitating from the solid solution layer, by supplying an etching gas to remove the metal from the solid solution layer while maintaining the solid solution temperature.

2. The production method according to claim 1, wherein a concentration distribution in a direction parallel to a surface of the substrate among concentration distributions of the carbon in the solid solution layer is made inhomogeneous, so as to grow the graphene in the direction parallel to the surface of the substrate.

3. A production method for graphene, wherein a line-shaped graphene grown in a first direction parallel to a surface of a substrate and directly attached to the surface is produced by the production method according to claim 2, and a planar graphene grown from the line-shaped graphene in a second direction parallel to the surface and directly attached to the surface is produced by the production method according to claim 2.

4. The production method according to claim 1, wherein in the forming step, a reducing agent that is able to reduce an oxide of the metal is supplied.

5. The production method according to claim 4, wherein in the forming step:

29

a metallic layer comprising the metal is formed on the substrate,
 an initial layer comprising carbon is formed on the formed metallic layer, and
 the formed initial layer and the formed metallic layer are heated to the solid solution temperature to form the solid solution layer.

6. The production method according to claim 4, wherein in the forming step:

an initial layer comprising a mixture of the metal and carbon is formed on the substrate, and
 the formed initial layer is heated to the solid solution temperature to form the solid solution layer.

7. The production method according to claim 4, wherein a concentration distribution of the supplied etching gas in a direction parallel to a surface of the substrate is made inhomogeneous, so as to grow the graphene in the direction parallel to the surface of the substrate.

8. The production method according to claim 4, wherein the substrate is a silicon dioxide substrate or a silicon substrate provided with a silicon dioxide layer on a surface,

the metal is iron, nickel, cobalt, or an alloy comprising the same, and

the etching gas is chlorine.

9. The production method according to claim 4, wherein in the forming step:

an initial layer comprising carbon is formed on the substrate,

a metallic layer comprising the metal is formed on the formed initial layer, and

the formed initial layer and the formed metallic layer are heated to the solid solution temperature to form the solid solution layer.

30

10. The production method according to claim 9, wherein in the forming step the initial layer is formed into a predetermined pattern, so as to form the graphene in the predetermined pattern.

11. The production method according to claim 9, wherein in the forming step the initial layer is formed to cover all or a part of a surface of the substrate, so as to form the graphene into a uniform continuous film covering all or a part of the surface of the substrate.

12. The production method according to claim 9, wherein the thickness of at least one of the formed initial layer and the formed metallic layer is made inhomogeneous, so as to make a concentration distribution in a direction parallel to a surface of the substrate among concentration distributions of the carbon in the solid solution layer inhomogeneous, and to grow the graphene in the direction parallel to the surface of the substrate.

13. The production method according to claim 12, wherein the thickness of the formed metallic layer is provided with a gradient, so as to grow the graphene in the direction of a component parallel to the surface of the substrate among directions of the gradient.

14. The production method according to claim 13, wherein the metallic layer comprises a first region extending parallel over a surface of the substrate and a second region extending parallel over a surface of the substrate, the two regions being connected by a constriction, the first region having smaller thickness of the metallic layer than the second region, and the second region being provided with a gradient in the thickness of the metallic layer, which increases with the distance from the constriction.

* * * * *